

07 CE CRP OVERCOAT ALL RAL SHADES

SAILENT FEATURES	These Quick Drying Paints have very good Drying Time. They have very good corrosion resistance.
RECOMMENDED USES	These Quick Drying Paints are used for Protection & Decoration of Steel Structures, Construction Machinery & Wooden Structures.
DIRECTION FOR USE	Adequate Surface Preparation and proper application is of Particular importance for achieving proper finish and Adhesion. Make sure that the Surface / Substrate to be painted should be free of Oil, Dust, Grease or any other foreign particles to get optimum adhesion & Finish. It Is necessary that the surface should be thoroughly cleaned either by scraping or wire brushing or sand blasting.

Sr. No	Tests	Specifications
1.	Skinning / Settling	No Skinning, Nil or Soft Settling
2.	Supply Viscosity	70 \pm 5 Sec @ 30°C OR as per customer specification
3.	Application By	Brush, Pot Gun or Air Less Spray Gun
4.	Application Viscosity	For Pot Spray Gun – 18 - 20 Sec. For Air Less Spray Gun – 22 – 25 Sec.
5.	Thinner Intake	0 to 10 % OR as per Customer Specification.
6.	Finish	Smooth, Uniform & free from Pin Holes & Orange Peels.
7.	Colour	As per ISC Shade Card, As per RAL Shade Card OR as per Customer Requirement.
8.	Fineness of Grind	7 + on Hegman Gauge
9.	Drying Time	Surface Dry – 20 – 30 Min Tack Free – 1 – 2 Hrs. Hard Dry – 6 – 8 Hrs. Over Coating Interval – Max 3 Hrs.
10.	Gloss	Egg Shell Gloss. Semi Glossy to Full Gloss.
11.	Specific Gravity	1.05 <u>+</u> 0.1 Kg/Lit
12.	Solid Content	Min 40 %
13.	Dry Film Thickness	30 – 50 Microns in Single Coat
14.	Theoretical Covering	8 – 10 M ² /Lit
15.	Practical Covering	5 – 6 M ² /Lit
16.	Scratch Hardness	1 – 2 Kg as per IS - 101
17.	Pencil Hardness	Passes for Min 2 H

TECHNICAL SPECIFICATION



07 CE CRP OVERCOAT ALL RAL SHADES

18.	Cross Cut Adhesion	100% adhesion as per ASTM D 3359
19.	Flexibility & Adhesion	No Such Scratch as to show bare metal
20.	Salt Spray Corrosion	After 240 Hrs. No Signs of Corrosion as per IS – 101 (Primer + Paint System)
21.	Flash Point	Not below 30 ^o C
22.	Impact Test	No paint Peel off
23.	Shelf Life	12 Month in a Sealed Condition from the date of Manufacturing.

HEALTH & SAFETY

SAFETY PRECAUTIONS	 As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and air mask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapors and paint mist by wearing suitable air mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. This as industrial product contains flammable materials and should be kept away from ignition sources; local safety regulations should be followed.
-----------------------	--

STORAGE & HANDLING

٠

STORAGE Store the paint in proper storage conditions as perpaint container in sealed conditions under shed extreme temperature. Do not stock paint mater Do not put back the half or unused material back the supplied paint, to avoid contamination. Handle	l, away from direct sunlight and rial near to any ignition sources. k in original container, containing

NOTE:- The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However as the product can be used under condition beyond our control, we can only guarantee the quality of the product itself.